


**SYNPO, akciová společnost, S. K. Neumanna 1316, 532 07 Pardubice, Zelené Předměstí, Česká republika**  
 Společnost je zapsána v Obchodním rejstříku u Krajského soudu v Hradci Králové, Oddíl B, vložka 627

## THE ASSESSMENT OF CORROSION PROTECTION OF STEEL STRUCTURES BY PROTECTIVE PAINT SYSTEMS

Producer of the Part: **Synpo a.s.**  
 Test performed by: SYNPO akciová společnost, S. K. Neumanna 1316, 532 07 Pardubice, Czech Republic  
 Test report: R013/200, performed in Pardubice on May 3, 2019

Substrate	Finish	Corrosivity category, durability ISO 12944-1,2	Requirements ISO 12944 -6	Meets
<b>Steel panel (cleanness St 3)</b>	LV AKZ 411  2K PUR paint 2 – 3 layers  (DFT 65 – 100 µm)	C3 – medium (durability 7 – 15 years)  C4 – low (durability to 7 years)	<b>ISO 6270-1</b> (120 h) + ISO 2409 (after 7 days) Ri 0, without blisters, cross-cut grade max. 2	<b>YES</b>
			<b>ISO 9227</b> (240 h) + ISO 2409 (after 7 days) Ri 0, without blisters, delamination ≤ 1,5 mm, cross-cut grade max. 2	<b>YES</b>
			<b>ISO 2409</b> grade max. 2	<b>YES</b>
Tested paint system <b>LV AKZ 411</b> meets requirements for corrosivity category:  <b>C3 – medium with durability 7 - 15 years</b> <b>C4 – low with durability to 7 years</b>				



**SYNPO, akciová společnost**  
**S.K. Neumanna 1316**  
**532 07 Pardubice**  
**DIČ: CZ46504711 ①**

Assessment made by:  
 In Pardubice on May 3, 2019

**Dipl. – Ing. Ondřej Janča**  
 Evaluation and Testing Department